# PAINTS, PRIMERS AND SPECIALISED COATINGS



#### **TECHNICAL DATA SHEET**

# **ANTI-SLIP STEP & RAMP PAINT**

TDS: CVW460B 118/W460

# DESCRIPTION: TYPICAL VISCOSITY:

Coo-Var Anti-Slip Step & Ramp Paint is used to provide a durable and hard wearing surface with an anti-slip finish. This product has been independently tested and has a PTV rating of 68 in dry conditions and 58 in wet. UK law recommends on a minimum Pendulum Test Value on floors of 36 dry, wet or contaminated. Suitable for indoor and outdoor use. Low odour & fast drying, hard wearing, water based and low

## **RECOMMENDED USE:**

slip risk in dry and wet conditions.

Coo-Var Anti-Slip Step & Ramp Paint can be used on concrete, wood, tarmac, stone, brickwork and suitably prepared metal.

## AVAILABILITY:

1 litre

#### FINISH:

Matt

# COLOUR:

Tile Red, Grey, Yellow, Black and Access Blue

## TYPICAL S.G. (SPECIFIC GRAVITY):

1.25 to 1.31 @ 20 °C

## **VOLUME SOLIDS:**

34 to 36%

#### WET FILM THICKNESS W.F.T

100 to 110 microns

## DRY FILM THICKNESS D.F.T

35 to 40 microns

# **EXPECTED SPREADING RATE:**

5 to 9 sq.m / litre

@ 35 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

2.5 Poise @ 25 °C

#### FLASH POINT:

Non-flammable

# DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1 hours @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

## MINIMUM OVERCOATING TIME:

6 hours

## **APPLICATION SPECIAL CONDITIONS:**

N/A

# **VOC CONTENT:**

max 41 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

# **APPLICATION DETAILS:**

Application Do not apply below 7 °C.

restrictions

Method: Brush or Roller

Thinner Clean water

(Max vol): (10%)

Nozzle size:

Nozzle N/A

pressure:

Cleaning solvent:

For further advice contact Coo-Var Technical Services on +44(0)1482 328053 The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

coo-var

Email: info@coo-var.co.uk www.coo-var.co.uk

Date printed 26 July 2018 Page 1 of 2

TDS: CVW460B 118/W460

Recoat

6 hours

interval:

## SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants. Concrete - power floated, granolithic and smooth surfaces should be roughened first to provide a good "key" for the paint. This can be done mechanically by abrading or blasting, or chemically, using Coo-Var Acid Etch. These processes will have the advantage in addition to preparing the surface of also removing dirt and laitance. New concrete must be allowed to cure thoroughly which can take up to 3 months. Other surfaces have to be prepared and primed with the suitable primer for that substrate. Existing painted surfaces -Surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose and flaking material and treat bare areas as new substrate and prepare

## MIXING INSTRUCTIONS:

Mix well before use.

# APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying. Do not paint when temperature will be at or below 7 °C during the painting and drying process.

# PRECEDING COAT:

Apply direct to wood, Coo-Var All Metals Primer on Metal, Coo-Var Anti-Slip Step & Ramp Paint thinned 5% with clean water on all other unpainted surfaces.

# SUBSEQUENT COAT:

Coo-Var Anti-Slip Step & Ramp Paint

## **REMARKS:**

Do not paint when temperature will be at or below 7 °C during the painting and drying process.

## **HEALTH AND SAFETY:**

See safety data sheet - SDS 20662

#### **ISSUED:**

14 June 2018

#### **REVISION:**

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053
The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-Var Email: info@coo-var.co.uk www.coo-var.co.uk

Page 2 of 2

Date printed 26 July 2018