Technical Data Sheet





Issue Date: Mar 23 Revision Date: N/A Page 1 of 2

Carbotread Exterior Floor Paint (Smooth)

Product Description	Carbotread Exterior Floor Paint (Smooth) is a tough, durable polyurethane oil based coating for the decoration and protection of exterior surfaces subjected to foot traffic. Provides a high covering smooth satin finish.									
Recommended Uses	such as concrete, and doorways. For	ior and interior use , wood and metal. T or other areas wher (Anti-Slip) option is	hese ir e moist	nclude ste	ps and sta	airways,	disabled ramps,			
VOC Content	380 <u>+</u> 20 g/litre									
Finish	Satin									
Volume Solids	55 ± 2% - Varies with colour									
Pack Sizes Available	1L - 2.5L - 5L									
Film Thickness & Coverage		Dry Film Thicknes	ss W	Wet Film Thickness		Theoretical Coverage				
	Minimum	44 µm	80 μm			12.5 m ² /litre				
	Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.									
Minimum Application Temperature	Air temperature 15°C Substrate temperature 10°C									
Drying & Overcoating Times	Applied to 30 r	nicrons DFT	s DFT +10°C		+20°C		+30°C			
	Touch Dry		8 hr		3 hr		2 hr			
	Hard Dry		48	hr	24 hr		r 24 hr			
	Full Hardness	Minimum		ays						
	Overcoating	Maximum	24	hr	16 hr		12 hr			
	Drying and re-coating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.									
Colour Range	A range of ready mixed colours, Ral Classic, BS 4800 and BS 381C.									
Product Code	1L - PPEFP1L - 2	2.5L - PPEFP2.5L	- 5L - P	PEFP5L						
Specific Gravity	0.9 - 1.2 kg/lt									
Storage Conditions	Between 15°C - 25°C for at least 12 hours prior to use. Do not allow to freeze.									
Shelf Life	Minimum 2 years if stored as above in unopened containers									
Flash Point	Above 38°C (closed cup)									
Surface Preparation	On previously painted surfaces, ensure it is sound and non-flaking. Abrade the surface preferably by mechanical abrasion to provide a "key" and maximise adhesion of the subsequent coating. For wood and metal surfaces treat as above and see preceding coat below for more information.									
Typical Viscosity	5 Poise @ 20 °C									





Issue Date: Mar 23 Revision Date: N/A Page 2 of 2

Carbotread Exterior Floor Paint (Smooth)

Mixing	Stir the paint with a drill stirrer or wooden baton at least 2" wide. Continue to stir during application to avoid settling of the product.								
Thinner	White Spirit Equipment Cleaner: White Spirit								
Application	Apply by brush, roller or spray and work well into the surface. Avoid applying the paint to thickly to avoid delaying drying times. The second and subsequent coats can be applied as soon as the first / preceding coat is dry usually after 12-24 hours, and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid power washing the surface for 7 days.								
Preceding Coat	For porous unpainted mature concrete, firstly apply a coat of Pliocem Concrete Sealer. For a more economical approach on porous surfaces, thin the first coat of Floor Paint with 10-15% of White Spirit and one neat coat. For wood, apply a clear universal preservative to untreated timber. For metal, prime with Palatine Anti Corrosive Metal Primer.								
Subsequent Coat	Applied in coats, until desired film thickness is achieved. Two undiluted coats are the minimum recommendation. For Heavy traffic areas use Palatine Two Pack Epoxy Floor Paint. Consult our technical team for more details.								
Application	Method	Airless Spray	Conventional Spray	Brush	Roller				
Methods		Yes	Yes	Yes	Yes				
	 Airless Spray: Output fluid pressure at tip 2000-3000 psi, .013015 - Gun Filter: Yellow Application by brush can achieve up to 55 microns dft. When applying by roller, use a solvent resistant sleeve. Avoid excessive film thickness as this will cause through-drying problems 								
Product Notes	the temperature is a		ctice. Care must be ta to avoid any contamin lication and drying.						
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from								

The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use

Palatine Paints & Chemicals Limited
55 Smallbrook Lane
Leigh
Lancashire
WN7 5PZ
TEL: 01942 884122

sales@palatinepaints.co.uk